

INDUSTRIAL PRODUCTS CHEMICAL RESISTANCE CHART

Bulletin No. 675E, Page 4

R – RESISTANT TO IMMERSION OR PROLONGED CONTACT
S – RESISTANT TO SPLASH AND SPILLAGE ONLY
N – NOT RECOMMENDED

	ALL CF PROD.	REPAIR COMPOUND	5020 FLOOR RESURFACER	WEAREX ARC	#6/#8	650	2001 SERIES	6700/	6470
TANNIC ACID	S	S	S	S	S	S	R	R	S
TARTARIC ACID	R	R	R	R	R	R	R	R	R
TETRACHLOROETHANE	N	N	N	N	N	N	R	S	N
TETRAETHYLENE PENTAMINE	R	R	R	R	R	S	R	S	R
TOLUENE SULFONIC ACID	S	S	S	S	S	N	S	R	S
TOLUENE	N	N	N	N	N	N	R	R	N
TRICHLOROACETIC ACID	N	N	S	N	N	N	N	N	N
TRICHLOROETHYLENE	N	N	N	N	N	N	R	S	N
TRISODIUM PHOSPHATE	R	R	R	R	R	R	R	R	R
TURPENTINE	N	N	N	N	N	N	S	R	N
UREA	R	S	R	S	R	S	S	R	S
URINE	R	R	R	R	R	R	R	R	R
VINEGAR	R	S	R	S	R	S	S	R	S
WATER, ACID, HOT, STEAM	S	N	S	S	S	N	N	S	N
WATER, BOILING	S	N	S	S	S	S	N	S	N
WAX EMULSION	R	R	R	R	R	R	R	R	R
WINE	R	S	R	S	R	R	R	R	S
XYLENE	R	S	R	S	R	R	R	R	S
ZINC CHLORIDE	S	S	S	S	S	S	R	R	S
ZINC SULFATE	S	S	S	S	S	S	R	R	S